

# Sealoflex Endura Balcony Coating - Summer and Winter Grades

## PRODUCT DATA

<b>Container sizes</b>	10 kg base resin
<b>Form</b>	Liquid
<b>Consumption</b>	Min. 3 kg per m <sup>2</sup>
<b>Rainproof</b>	Approx. 45 minutes*
<b>Walkable</b>	Approx. 1 hour*
<b>Overcoating</b>	Approx. 1 hour*
<b>Withstand stress</b>	Approx. 3 hours*
<b>Pot life</b>	Approx. 15 minutes*
<b>Shelf life</b>	Min. 6 months**
<b>Colour</b>	Blue / Grey (RAL 7031)

\* Times given are reduced with higher (and increased with lower) surrounding and work surface temperatures. Values attained at 20 °C.

\*\* If stored in original container.

## INTENDED USE

Sealoflex Endura Balcony Coating is used as the waterproofing layer with Sealoflex Endura Reinforcing Fabric for balconies and roof terrace applications.

## DESCRIPTION

Sealoflex Endura Balcony Coating is an exceptionally fast curing, cold liquid applied two-component coating comprising resin and catalyst.

- Elastomeric
- Vapour permeable
- Chemical and UV resistant
- Hydrolysis and alkali hydrolysis resistant
- Mechanically resistant
- Solvent and isocyanate free

## SURFACE PREPARATION

Ensure that the substrate is clean, dry and free from dust, laitance, grease, oil and any other contaminants and assess / pre-treat / prepare substrate in accordance with Sealoflex Endura specification.

## APPLICATION CONDITIONS

Apply only when atmospheric and substrate temperatures are 0 °C to 35 °C, with up to 95% RH. The surface of the substrate should be clean and dry and must be 3 °C above the dew point.

Personal Protective Equipment (PPE) should be worn.

## INITIAL RESIN MIXING

- Thoroughly mix the Sealoflex Endura Balcony Coating resin in the drum with a slow speed mixer until the resin achieves a uniform consistency.
- If required, decant a measured weight of resin into a suitable container.

## MIXING RATIO

Measure the appropriate weight of catalyst for the weight of resin and the temperature. Add the catalyst to the pre-mixed / decanted resin and thoroughly mix using a slow speed mixer for a minimum 2 minutes until the catalyst has been evenly distributed. Leave for a minimum of 1 minute to allow the catalyst to fully dissolve. Re-mix and use the mixed material within the pot life.

Temperature range of:

- 0 °C to +15 °C 20 kg resin + 0.80 kg catalyst (4%)
- +15 °C to +35 °C 20 kg resin + 0.40 kg catalyst (2%)

## CONSUMPTION

The approximate consumption for Sealoflex Endura Balcony Coating is 3 kg/m<sup>2</sup> when used with Sealoflex Endura Reinforcing Fabric.

## APPLICATION METHOD

Apply the mixed Sealoflex Endura Balcony Coating onto the prepared substrate with a roller.

### Interruptions During Works

Unless the surface is fully aggregate filled, if work is interrupted for more than 12 hours or if soiled by rain etc., use Sealoflex Endura Cleaner to clean and reactivate the transition area. Overlay after Sealoflex Endura Cleaner has evaporated and a minimum 20 minutes / maximum 60 minutes after application. If the surface is aggregate filled ensure that the surface is clean, dry and free from dust, grease, oil and any other contaminants prior to overlay.

## CLEANING

Clean tools immediately after use with Sealoflex Endura Cleaner. Wash hands thoroughly after use.

## STORAGE

Can be stored unopened and unmixed for approximately 6 months in a cool, dry place above freezing. Keep container away from direct sunlight when in storage and on the construction site.

## HEALTH & SAFETY

Information regarding transportation, handling, storage and disposal can be found on the Safety Data Sheet and on the label of the container. All recommendations and warnings must be observed.

## TECHNICAL SERVICES

Specialist advice and design guidance on all matters relating to the Sealoflex Endura System is freely available from our Technical Services Team.

### **BMI UK & Ireland**

BMI House  
2 Pitfield  
Kiln Farm  
Milton Keynes  
MK11 3LW  
+44 (0) 1908 015760

We are committed to continuously enhancing and improving our product range. We reserve the right to change our product specifications. We reserve the right to correct any typographical or clerical error or omission. For the latest information contact customer service.