

Sealoflex Prima Speedshot

Sealoflex Prima Speedshot is a specially engineered accelerant provided in an easy to use applicator bottle, specifically for the Sealoflex Prima Waterproof Coating.

PRODUCT DATA

| | |
|-----------------------|--------------|
| Container size | 900 ml |
| Form | Liquid |
| Colour | Blue / Green |

INTENDED USE

Sealoflex Prima Speedshot accelerates the curing time of the Sealoflex Prima Waterproof Coating at surface and ambient temperatures of between +5 °C and +10 °C. It is the ideal solution where time is of the essence. Common applications where Sealoflex Prima Speedshot may be utilised include walkways and balconies where pedestrian traffic is required at the earliest opportunity.

APPLICATION CONDITIONS

Apply only when atmospheric and substrate temperatures are greater than 5 °C. The surface of the substrate should be clean and dry and must be 3 °C above the dew point. If the surface is below or at dew point temperature then moisture can form at the surface and affect coating adhesion and curing.

Personal Protective Equipment (PPE) should be worn.

PRODUCT TESTING

BMI Sealoflex Prima has been independently site and laboratory tested by the British Board of Agrément and awarded BBA certificate number 13/5028.



APPLICATION METHOD

Remove the blue cap and squeeze the bottle several times until the liquid reaches the 25ml (1 shot) line in the dosage chamber. Add the appropriate number of single shots to the Sealoflex Prima Waterproof Coating as required. Refer to the table below for confirmation of the number of shots required. Following application of the Sealoflex Prima Speedshot, install the waterproof coating in the usual 'wet-on-wet' application method, taking care to observe the accelerated working times.

WORKABILITY PERIOD

| Temp | | 25 ml (1 shot) | 50 ml (2 shots) | 75 ml (3 shots) |
|-------|--------------------|-------------------|--------------------|--------------------|
| 5 °C | Working time | N/A | N/A | 22 mins. |
| | Follow on coatings | N/A | N/A | 4.5 hrs. |
| 10 °C | Working time | N/A | N/A | 22 mins. |
| | Follow on coatings | N/A | N/A | 4.5 hrs. |
| 20 °C | Working time | 20 mins. | 18 mins. | N/A |
| | Follow on coatings | 7 hrs. | 6 hrs. | N/A |

For comparison, the standard workability period is approx. 30 minutes at 23 °C for the Sealoflex Prima Coating without accelerant.

CLEANING

Clean tools immediately after use using Sealoflex MEK Cleaner. Wash hands thoroughly after use.

QUALITY ASSURANCE

Sealoflex Prima products are supplied under a Quality Management System approved to EN ISO 9001: 2015 by TÜV NORD CERT GmbH.



STORAGE

Containers should be stored in a dry and cool environment on a flat, level, and clean surface away from sources of ignition, including pilot lights and sparks. Protect the product against moisture, direct sunlight and extremes of temperature.

Keep containers tightly closed when not in use. In original unopened containers the shelf life is 12 months.

DISPOSAL

Liquid EWC 07 02 04

HEALTH & SAFETY

Health & Safety information supplied by manufacturer must be observed. Do not allow into the sewer system or ground.

TECHNICAL SERVICES

Specialist advice and design guidance on all matters relating to Sealoflex Prima systems is freely available from our Technical Services Team.

Sealoflex Prima System components are manufactured under licence from Kemper System GmbH & Co. KG.

BMI UK & Ireland

BMI House
2 Pitfield
Kiln Farm
Milton Keynes
MK11 3LW
+44 (0) 1908 015760

We are committed to continuously enhancing and improving our product range. We reserve the right to change our product specifications. We reserve the right to correct any typographical or clerical error or omission. For the latest information contact customer service.